

English

CreatorSilk

2 Side Coated Silk

Property		Units	Tolerance	Tolerance															
				90	100	115	125	130	135	150	170	200	225	250	270	300	350		
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	
Thickness	ISO 534	TAPPI T411	µm	± 4%	80	86	100	107	111	115	131	152	181	210	239	263	299	358	
Whiteness CIE	ISO 11475		%	± 3	120	120	120	120	120	120	120	120	120	120	120	120	120	120	
Opacity	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	95,0	95,5	96,0	96,0	97,0	97,5	-	-	-	-	-	-	
Smoothness Bekk	ISO 5627	TAPPI T475	s	± 40%	210	210	220	220	220	220	200	160	160	130	120	120	100	100	
Relative Humidity		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

- Last updated: **06-03-12**
- Values are subject to change without notice.

Español

CreatorSilk

Estucado 2 Caras Semimate

Propiedad		Unidades	Tolerancia	Tolerancia															
				90	100	115	125	130	135	150	170	200	225	250	270	300	350		
Gramaje	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	
Calibre	ISO 534	TAPPI T411	µm	± 4%	80	86	100	107	111	115	131	152	181	210	239	263	299	358	
Blancura CIE	ISO 11475		%	± 3	120	120	120	120	120	120	120	120	120	120	120	120	120	120	
Opacidad	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	95,0	95,5	96,0	96,0	97,0	97,5	-	-	-	-	-	-	
Lisura Bekk	ISO 5627	TAPPI T475	s	± 40%	210	210	220	220	220	220	200	160	160	130	120	120	100	100	
Humedad relativa		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

- Última actualización: **06-03-12**
- Los valores están sujetos a cambio sin aviso previo.

Français

CreatorSilk

Couché 2 Faces Demi-mat

Propriété		Unités	Tolérance	Tolérance															
				90	100	115	125	130	135	150	170	200	225	250	270	300	350		
Grammage	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	80	86	100	107	111	115	131	152	181	210	239	263	299	358	
Blancheur CIE W	ISO 11475		%	± 3	120	120	120	120	120	120	120	120	120	120	120	120	120	120	
Opacité	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	95,0	95,5	96,0	96,0	97,0	97,5	-	-	-	-	-	-	
Lissé Bekk	ISO 5627	TAPPI T475	s	± 40%	210	210	220	220	220	220	200	160	160	130	120	120	100	100	
Humidité relative		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

- Dernière actualisation: **06-03-12**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português

CreatorSilk

Couché 2 Faces Semi-mate

Propriedade		Unidade	Tolerância	Tolerância															
				90	100	115	125	130	135	150	170	200	225	250	270	300	350		
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	
Calibre	ISO 534	TAPPI T411	µm	± 4%	80	86	100	107	111	115	131	152	181	210	239	263	299	358	
Brancura CIE	ISO 11475		%	± 3	120	120	120	120	120	120	120	120	120	120	120	120	120	120	
Opacidade	ISO 2471	TAPPI T519	%	-2.0	92,0	93,0	95,0	95,5	96,0	96,0	97,0	97,5	-	-	-	-	-	-	
Lisura Bekk	ISO 5627	TAPPI T475	s	± 40%	210	210	220	220	220	220	200	160	160	130	120	120	100	100	
Humidade relativa		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

- Última actualização: **06-03-12**
- Os valores estão sujeitos a mudanças sem pré-aviso.