

English

## CreatorStar

### 2 Side Coated Gloss

Property			Units	Tolerance	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Thickness	ISO 534	TAPPI T411	µm	± 4%	69	78	89	91	95	100	110	125	148	171	190	205	232	285
Whiteness CIE	ISO 11475		%	± 3	119	119	119	119	119	119	119	119	119	119	119	119	119	119
Opacity	ISO 2471	TAPPI T519	%	-2.0	91,0	92,5	94,5	93,5	95,0	95,5	96,5	97,0	-	-	-	-	-	-
Paper Gloss	ISO 8254-1	TAPPI T480	%	± 5	66	67	68	72	72	72	73	74	74	74	74	74	74	74
Smoothness Bekk	ISO 5627	TAPPI T475	s	± 40%	1200	1040	950	1100	1000	1000	1000	850	600	550	500	400	350	250
Relative Humidity		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Last updated: **06-03-12**
- Values are subject to change without notice.

Español

## CreatorStar

### Estucado 2 Caras Brillante

Propiedad			Unidades	Tolerancia	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Gramaje	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	TAPPI T411	µm	± 4%	69	78	89	91	95	100	110	125	148	171	190	205	232	285
Blancura CIE	ISO 11475		%	± 3	119	119	119	119	119	119	119	119	119	119	119	119	119	119
Opacidad	ISO 2471	TAPPI T519	%	-2.0	91,0	92,5	94,5	93,5	95,0	95,5	96,5	97,0	-	-	-	-	-	-
Brillo de papel	ISO 8254-1	TAPPI T480	%	± 5	66	67	68	72	72	72	73	74	74	74	74	74	74	74
Lisura Bekk	ISO 5627	TAPPI T475	s	± 40%	1200	1040	950	1100	1000	1000	1000	850	600	550	500	400	350	250
Humedad relativa		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última actualización: **06-03-12**
- Los valores están sujetos a cambio sin aviso previo.

Français

## CreatorStar

### Couché 2 Faces Brillant

Propriété			Unités	Tolérance	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Grammage	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	69	78	89	91	95	100	110	125	148	171	190	205	232	285
Blancheur CIE W	ISO 11475		%	± 3	119	119	119	119	119	119	119	119	119	119	119	119	119	119
Opacité	ISO 2471	TAPPI T519	%	-2.0	91,0	92,5	94,5	93,5	95,0	95,5	96,5	97,0	-	-	-	-	-	-
Brillance du papier	ISO 8254-1	TAPPI T480	%	± 5	66	67	68	72	72	72	73	74	74	74	74	74	74	74
Lissé Bekk	ISO 5627	TAPPI T475	s	± 40%	1200	1100	950	1100	1000	1000	800	800	500	500	400	300	300	200
Humidité relative		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Dernière actualisation: **06-03-12**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português

## CreatorStar

### Couché 2 Faces Brilhante

Propriedade			Unidade	Tolerância	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	TAPPI T411	µm	± 4%	69	78	89	91	95	100	110	125	148	171	190	205	232	285
Brancura CIE	ISO 11475		%	± 3	119	119	119	119	119	119	119	119	119	119	119	119	119	119
Opacidade	ISO 2471	TAPPI T519	%	-2.0	91,0	92,5	94,5	93,5	95,0	95,5	96,5	97,0	-	-	-	-	-	-
Brilho do papel	ISO 8254-1	TAPPI T480	%	± 5	66	67	68	72	72	72	73	74	74	74	74	74	74	74
Lisura Bekk	ISO 5627	TAPPI T475	s	± 40%	1200	1040	950	1100	1000	1000	1000	850	600	550	500	400	350	250
Humidade relativa		TAPPI T502	%	± 7%	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última atualização: **06-03-12**
- Os valores estão sujeitos a mudanças sem pré-aviso.